





Q 70-250


2K HS AS Clear Coat 2:1


Characteristics


70-250 High-filling 2-component acrylic clearcoat with UV protection, which ensures high gloss and protection on solventbased and water-based basecoats. Ideally suited for use in spot repair work as well as for complete paintwork. High resistance to weather, environmental influences and chemicals, resistant to yellowing, durable gloss retention. In addition, 70-250 Clear Coat provides excellent polishing properties.

Physical Characteristics


 12 month

 n/a

 2:1 + 0-10%
70-205HN / 70-205HF

Application


 18 - 20 s
4 mm DIN


 1,2 - 1,3 mm
2,0 - 2,5 bar

 HVLP 1,2 - 1,3 mm
2,0 - 2,5 bar

Consumption: 6 - 8 m²/l


 1 - 2

 Between the coatings 5 - 10 min
Before the oven drying 10 - 15 min

 40 - 60 μm

Drying




 dust free: 30 - 40 min
set to touch: 6 - 8 h
ready for assembly 24 h

set to touch: 30 min
ready for assembly 2 h

shortwave 8 Minuten
mediumwave 10 - 15 Minuten


20°
1 h with 70-205HF Hardener fast
4 h with 70-205 HN Hardener normal

Storage

 Store the product in a ventilated place. Keep away from direct exposure to sunlight. Keep between +5°C and 20°C.

Safety

   For more informations check the safety data sheet.

 This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.