




# Q 70-435

# Bumper Paint / Bumper Paint Aerosol

## Characteristics

70-435 is a one-component textured coating to repair bumpers, trim strips, exterior mirrors etc. and to paint commonly used plastic substrates in the automotive industry Direct adhesion on cleaned and sanded plastic parts made of ABS, ABS-PC, PP-EPDM, PUR-RIM, PUR, hard PVC. Fast drying and easy application as well as good weather resistance are the characteristics of this product. Temperature-resistant up to 70 °C.

## Physical Characteristics



12 month



400 ml: 2004/42/IB(e)(840)<840  
1000 ml: 2004/42/IB(e)(840)<539



**1000 ml:**  
Thinner for 70-453 Bumper Paint,  
addition 10 - 15 %

## Application 400 ml Aerosol



cleaning



shake well for  
2 min



15 cm - 20 cm



1  
15 - 20 µm



10 min  
between coatings




clean valve

## Application 1000 ml



cleaning



18 - 22 s  
4 mm DIN




1,6 - 1,8 mm  
2,0 - 2,5 bar



2



1. 5 - 8 min.  
2. 10 - 15 min.



40 - 50 µm

## Drying



400 ml  
Aerosol



dust dry: 7 min  
set to touch: 15 min



1000 ml

dust dry: 20 min  
set to touch: 60 min  
ready for assembly 24 h

## Storage



Store the product in a ventilated place. Keep away from direct exposure to sunlight. Keep between +15°C and 25°C.

## Safety



For more informations check the safety data sheet.



This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.